



**Attika**  
Resin's expert

Attika LLC  
187000,  
Russia, Leningrad region., Fedorovskoe S. p., d.  
Annolovo, 2nd Vertical passage, 9  
Tel / Fax: +7 (812) 441-21-80  
www.attikarus.ru


## Attcure RD 24

### Properties:

- Active tinner for epoxy resins
- Hydrofobic

### Foundation:

Glysidyl ether (monofunctional)



### Application

- Coatings, floors and mortars for civil engineering
- Paints and varnishes

### Technical specifications

| Specification                   | Measurement unit       | Value       |
|---------------------------------|------------------------|-------------|
| Epoxy equivalent                | g/equiv                | 270-313     |
| Epoxy number                    | Equiv/100g.            | 0,32-0,37   |
| Viscosity                       | MPa/s                  | 5-10        |
| Refractive index [ $n_d$ 25 °C] | -                      | 1,444-1,450 |
| Color                           | Gardner                | 1           |
| Density                         | $\text{g}/\text{cm}^3$ | 0.88-0,91   |
| Epychlorohydrin content         | ppm                    | Max. 10     |
| Flash point                     | °C                     | near 150    |

### Storage:

- Shelf life is 12 months from the date of manufacture. Store in a cool and dry place.

### Packing:

- Barrels 200 kg.
- Cubes 1000 kg.