



**Attika**  
Resin's expert

Attika LLC  
187000,  
Russia, Leningrad region., Fedorovskoe S. p., d.  
Annolovo, 2nd Vertical passage, 9  
Tel / Fax: +7 (812) 441-21-80  
www.attikarus.ru

## ATTICURE RD 3

### Properties:

- Active tinner for epoxy resins

### Foundation:

Diglycidyl ether 1,4-butanediol

### Application

- Coatings, primers and epoxy polymer solutions for construction, painting  
-High chemical resistance paints  
-Pitches for pouring  
-Binding for composites

### Technical specifications

Specification	Measurement unit	Value
Epoxy equivalent	g/equiv	130-145
Epoxy number	Equiv/100g.	0,69-0,77
Viscosity (23°C)	mPas	12-22
Refractive index (nD25°C)	-	1,457-1,463
Density (25°C)	g/cm <sup>3</sup>	1,10-1,12
The percentage of hydrolyzable chlorine	%	Max 0,2
Color index	Gardner	Max 1
Epychlorohydrin content	Ppm	Max 10
Flash point	°C	CA.170
LD50, for rats 24h	Mg/kg	3000
Vapor pressure	mBar	1,3

### Storage:

- Shelf life is 12 months from the date of manufacture. Store in a cool and dry place.

### Safety requirements:

When working with epoxy resins and hardeners, the precautions specified in the safety data sheet must be observed. Avoid contact with exposed skin. If necessary, wash the contamination with warm water and soap.

Wear protective clothing and use a barrier cream before starting work. Ensure that all safety instructions comply with local and federal laws.

### Packing

Drums 200 kg  
IBC containers 1000 kg  
Filing